

490 W. Lenni Rd. | Lenni, PA 19052 | PH 610.459.1000 | TF 800.999.1700 | FX 610.459.1084 westlakeplastics.com



ABSYLUX® ACRYLONITRILE-BUTADIENE-STYRENE

Absylux ABS is a low cost engineering plastic that is easy to machine and fabricate. Absylux is an ideal material for structural applications when impact resistance, strength, and stiffness are required. It is widely used for machining pre-production prototypes since it has excellent dimensional stability and is easy to paint and glue. Natural (beige) and black Absylux are FDA compliant for use in food processing applications.

The following physical property information is based on typical values of the base acrylonitrile-butadienestyrene resin.

Applications Include:

- Machined prototypes
- Structural components
- Support blocks
- Housings
- Covers

Advantages of Absylux:

Excellent impact resistance

- Good machinability
- Excellent aesthetic qualities
- Easy to paint and glue
- Good strength and stiffness
- Low cost

Manufacturing Capabilities:

- **Rod:** ¹/₄" to 8" dia.
- **Sheet:** ¹/₁₆" to ¹/₄" thick
- **Slab:** ³/₈" to 6" thick
- Film: .001" to .029" thick

Colors/Grades:

- Natural (white) FDA/FR
- Black FDA/FR

In addition to our standard capabilities, Westlake also has the ability to process custom resins in various sizes and colors with some exceptions.

Property	Units	Test Standard	Unfilled	Flame Retardant (FR)
• •				
Mechanical				
Flexural Modulus	psi	ASTM D790	314,000	300,000
Flexural Strength @yield	psi	ASTM D790	9,700	8,800
Hardness	R Scale	ASTM D785	R105	R100
Izod Impact Strength Notched @-22°F Notched @73°F	ft•lbs/in ft•lbs/in	ASTM D256 ASTM D256	11 16	 4.0
Tensile Modulus	psi	ASTM D638	302,000	320,000
Tensile Strength @yield	psi	ASTM D638	5,800	5,530
Thermal				
Flammability Rating— @.0625" @.098"		UL94 UL94	HB (.060") —	V-0 5V-A
Heat Deflection Temperature @66 psi @264 psi	°F °F	ASTM D648 ASTM D648	200 177	 163
Other				
Specific Gravity	_	ASTM D792	1.03	1.19

This information is offered solely for your consideration, examination and verification, and is to be construed neither as a warranty nor guarantee that the same results as those stated herein will be obtained by the use to which others may put the material. Each user of the material should make his own tests to determine the characteristics and suitability of the material for his own particular use and the use which will be made of the completed product. This publication is not to be taken as a license to operate under, or a recommendation to infringe any patents. The observance of all legal regulations and patents is the responsibility of the user. The buyer's exclusive remedy against the seller shall be for the repair or replacement of defective stock. No other remedy (including, but not limited to, incidental or consequential damages for lost profits, lost sales, injury to person or property, or other incidental or consequential loss) shall be available to the buyer. EXCLUSION OF WARRANTIES: THERE ARE NO WARRANTIES AS TO THE MATERIAL DESCRIBED HEREIN, EITHER EXPRESSED OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, ANY WARRANTY OF MERCHANTABILITY OR FITNESS FOR PARTICULAR PURPOSE. ANY VALUES STATED IN SELLER'S LITERATURE ARE TYPICAL PROPERTIES ONLY.