

## TECAFORM® AD HPV13 - Stock Shapes

### Chemical Designation

POM-H (Polyacetal (Homopolymer))

### Colour

brown

### Density

1.5 g/cm<sup>3</sup>

### Fillers

PTFE powder

### Main features

- very good slide and wear properties
- good mechanical properties
- good machinability
- good chemical resistance
- low water absorption
- good dimensional stability

### Target Industries

- food engineering
- power engineering
- conveyor technology
- gear manufacturing
- business machines
- packaging and paper machinery

<i>Mechanical properties</i>	<i>condition</i>	<i>value</i>		<i>test method</i>	<i>comment</i>
Modulus of elasticity (tensile test)	@ 73 °F	340,000	psi	ASTM D 638	
Tensile strength at yield	@ 73 °F	7000	psi	ASTM D 638	
Tensile strength at break	@ 73 °F	7000	psi	ASTM D 638	
Elongation at break	@ 73 °F	10	%	ASTM D 638	
Flexural strength	@ 73 °F	12,500	psi	ASTM D 790	
Modulus of elasticity (flexural test)	@ 73 °F	350,000	psi	ASTM D 790	
Impact strength (Izod)	@ 73 °F	1.0	ft-lbs/in	ASTM D 256	
Rockwell hardness	R Scale @ 73 °F	118		ASTM D 785	
Coefficient of friction	Static	0.07	%	ASTM D 3702	
Coefficient of friction	Dynamic, 40 psi, 50 fpm	0.12	%	ASTM D 3702	
Wear rate	Against Steel, 40 psi, 50 fpm	20*10 <sup>-10</sup>	in <sup>3</sup> -min/ft-lbs-hr	ASTM D 3702	
<i>Thermal properties</i>	<i>condition</i>	<i>value</i>		<i>test method</i>	<i>comment</i>
Melting temperature		347	°F	-	
Deflection temperature	@264 psi	244	°F	ASTM D 648	
Deflection temperature	@ 66 psi	334	°F	ASTM D 648	
Service temperature	Long Term	185	°F	-	
Thermal expansion (CLTE)		5.1*10 <sup>-5</sup>	in/in/°F	ASTM D 696	
<i>Other properties</i>	<i>condition</i>	<i>value</i>		<i>test method</i>	<i>comment</i>
Limiting PV	@ 100 fpm	1,600	ft-lbs/min	-	
Limiting PV	@ 10 fpm	12,000	ft-lbs/min	-	
Moisture absorption	@ 24 hrs, 73 °F	.11	%	ASTM D 570	

→ Resin specification:  
ASTM D6778-06 POM110 L13 B57230 superseding ASTM D4181-00 POM110L13A00000  
Shapes specification:  
ASTM D6100-11 S-POM0132

This information reflects the current state of our knowledge and is intended only to assist and advise. It is given without obligation or liability. It does not assure or guarantee chemical resistance, quality of products or their suitability in any legally binding way. Values are not minimum or maximum values, but guidelines that can be used for comparative purposes in material selection. They are within the normal range of product properties and do not represent guaranteed property values. Testing under individual application circumstances is always recommended. Data is obtained from extruded shapes material unless otherwise noted. References to FDA compliance refer to the resins from which the products were made unless otherwise noted. All trade and patent rights should be observed. All rights reserved. Data sheet values are subject to periodic review, the most recent update can be found at [www.ensinger-inc.com](http://www.ensinger-inc.com).